

## TEST REPORT

REPORT NUMBER : TURR120089458

APPLICANT NAME Durfoam İzolasyon ve Ambalaj San. A.Ş.

ADDRESS Akçalar San. Böl. Şirşır Cad. No: 5 Bursa TÜRKİYE  
FAX NO :0224 484 23 21  
Attention :Taner Ömeroğlu (tomeroğlu@durfoam.com)

## SAMPLE DESCRIPTION :

- Sample 1 One sample of IXPE 1mm 67 kg/m3 White foam  
Sample 2 One sample of IXPE 2mm-4mm-6mm 33 kg/m3 White foam  
Sample 3 One sample of IXPE 1mm 67 kg/m3 Anthracite foam  
Sample 4 One sample of IXPE 2mm-3mm-5mm-6mm-9mm 33 kg/m3 Anthracite foam

DATE IN : 25 July, 2012

DATE OUT : 27 July, 2012

REQUEST : RoHS Test was performed on the items.

RESULTS : See attachment

## CONCLUSION :

Testing Item	Conclusion
Sample 1	PASS
Sample 2	PASS
Sample 3	PASS
Sample 4	PASS

The test results relate only to the items tested. The whole and/or the part of this test report shall not be reproduced and shall not be shared with third parties, nor to be used for PR activities without the written permission of INTERTEK Test Hizmetleri A.Ş.  
The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor k=2, providing a level of confidence of approximately 95%. The uncertainty evaluation has been carried out in accordance with ISO/IEC 17025 and UKAS accreditation requirements. Unless otherwise is specified, all Pass or Fail results are given without uncertainty considered. When uncertainty is taken into account, the result may be borderline. Borderline results need to be re-tested to determine their disposition up to customer's decision. Opinions and interpretations expressed herein are outside the scope of UKAS accreditation. Tests marked (\*) in this test report are not included in the UKAS accreditation schedule for this laboratory.

Bora Şirinbilek  
CoordinatorNeslihan Sözer  
Chemical Laboratory Manager

2111

Intertek Test Hizmetleri A.Ş.

Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone: +90.212. 496 46 46 Fax: +90.212. 452 80 55

e-mail : labtest.turkey@intertek.com

[www.intertek-cg-tur.com](http://www.intertek-cg-tur.com)

120089458



**(A) Test Method Summary**

Testing Item	Result				RoHS Limit (ppm)
	Sample 1	Sample 2	Sample 3	Sample 4	
Cadmium (Cd) Content	ND	ND	ND	ND	0.01 % (100 ppm)
Chromium VI (Cr+6) Content (ppm) (for non - metal)	ND	ND	ND	ND	0.1 % (1000 ppm)
Lead (Pb) Content	ND	ND	ND	ND	0.1 % (1000 ppm)
Mercury (Hg) Content	ND	ND	ND	ND	0.1 % (1000 ppm)
<b>Flame Retardants</b>					<b>0.1 % (1000 ppm)</b>
<b>Polybrominated Biphenyls (PBB)</b>	<b>ND</b>	<b>ND</b>	<b>ND</b>	<b>ND</b>	
Monobromobiphenyl (MonoBB)	ND	ND	ND	ND	
Dibromobiphenyl (DiBB)	ND	ND	ND	ND	
Tribromobiphenyl (TriBB)	ND	ND	ND	ND	
Tetrabromobiphenyl (TetraBB)	ND	ND	ND	ND	
Pentabromobiphenyl (PentaBB)	ND	ND	ND	ND	
Hexabromobiphenyl (HexaBB)	ND	ND	ND	ND	
Heptabromobiphenyl (HeptaBB)	ND	ND	ND	ND	
Octabromobiphenyl (OctaBB)	ND	ND	ND	ND	
Nonabromobiphenyl (NonaBB)	ND	ND	ND	ND	
Decabromobiphenyl (DecaBB)	ND	ND	ND	ND	
<b>Polybrominated Diphenyl Ethers (PBDE)</b>	<b>ND</b>	<b>ND</b>	<b>ND</b>	<b>ND</b>	
Monobromodiphenyl Ether (MonoBDE)	ND	ND	ND	ND	
Dibromodiphenyl Ether (DiBDE)	ND	ND	ND	ND	
Tribromodiphenyl Ether (TriBDE)	ND	ND	ND	ND	
Tetrabromodiphenyl Ether (TetraBDE)	ND	ND	ND	ND	
Pentabromodiphenyl Ether (PentaBDE)	ND	ND	ND	ND	
Hexabromodiphenyl Ether (HexaBDE)	ND	ND	ND	ND	
Heptabromodiphenyl Ether (HeptaBDE)	ND	ND	ND	ND	
Octabromodiphenyl Ether (OctaBDE)	ND	ND	ND	ND	
Nonabromodiphenyl Ether (NonaBDE)	ND	ND	ND	ND	
Decabromodiphenyl Ether (DecaBDE)	ND	ND	ND	ND	

Remarks : ppm=Parts per million based on dry weight of sample  
 µg/cm²=Microgram per square centimetre  
 mg/kg with 50 cm²=Milligram per kilogram with 50 square centimetre  
 <=Less than  
 ND =Not detected      NA =Not applicable      NR =Not requested

**(B) Test Method :**

Testing Item	Testing Method	Reporting Limit
Cadmium (Cd)Content	With reference to IEC 62321:2008,by acid digestion and determined by ICP-OES	2 ppm
Lead (Pb)Content	With reference to IEC 62321:2008,by acid digestion and determined by ICP-OES	2 ppm
Mercury (Hg)Content	With reference to IEC 62321:2008,by acid digestion and determined by ICP-OES	2 ppm
Chromium VI (Cr6+)(For non-metal)	With reference to IEC 62321:2008,by alkaline digestion and determined by UV-VIS spectrophotometer	1 ppm
Chromium VI (Cr6+)(For metal)	With reference to IEC 62321:2008,by SPOT TEST	1 ppm (IN TESTING SOLUTION)
Chromium VI (Cr6+)(For metal)	With reference to IEC 62321:2008 ,by boiling water extraction and determined by UV-VIS spectrophotometer	0.02 mg/kg with 50 cm² (IN TESTING SOLUTION)
PBBs/PBDES	With reference to IEC 62321:2008,by solvent extraction and determined by GC/MS and HPLC	5 ppm

NOTE : The above limits were quoted from 2002/95/EC and amendment 2005/618/EC for homogeneous material.






**Sample 1**




**Sample 2**



**Sample 3**



**Sample 4**



## END OF TEST REPORT ##



2111

**Intertek Test Hizmetleri A.S.**

Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone : +90.212. 496 46 46 Fax : +90.212. 452 80 55

e-mail : [labtest.turkey@intertek.com](mailto:labtest.turkey@intertek.com)

[www.intertek-cq-tur.com](http://www.intertek-cq-tur.com)